



**FLOOR CARE**

# W-75™

**floor finish**

## TECHNICAL DATA SHEET

**Packaging Code**

4 x 4 L  
 (4x1.06 US gal) 2389278001  
 20 L  
 (5.28 US gal) 2389334001  
 210 L  
 (55.48 US gal) 2389390001

**Description:**

W-75 is formulated to work with any maintenance method and equipment on all types of floors. It offers good gloss characteristics along with durability making it the number one choice of school boards and institutions where spray-buffing maintenance schedules and budgets are restricted. W-75 offers fast drying properties so down time is at a minimal and it responds well to burnishing.

**Use Direction:**

Completely remove old finish and sealer from the floor using an Avmor Floor Stripper and rinse thoroughly. When floor is dry apply 2-3 uniform coats of finish. Allow 30 minutes drying time between coats.

DRY MOPPING: Remove loose dirt and grit with a dust mop. If required, apply 1-2 coats of EP86 Lokseal Floor Sealer.

WET MOPPING: Use an Avmor neutral cleaner as directed.

SPRAY BUFFING: Ensure a minimum base of 2-3 coats of finish is on the floor. Use a 50-50 mixture of finish W-75 or use EP85 Sidekick as directed.

**Precautions for Food Plants:**

Must be applied in keeping with manufacturers' recommendations for application on hard smooth level surfaces. To avert possible adverse organoleptic effects in food, which are processed in the area, adequate precautions should be taken to ensure that the volatile constituents of the applied products do not contaminate the foods.

**Security:**

|                     |               |
|---------------------|---------------|
| HEALTH              | 1             |
| FLAMMABILITY        | 0             |
| REACTIVITY          | 0             |
| PERSONAL PROTECTION | X             |
| X =                 | See SDS       |
| 0 =                 | Insignificant |
| 1 =                 | Slight        |
| 2 =                 | Moderate      |
| 3 =                 | High          |
| 4 =                 | Extreme       |

**Note:**

The data presented herein is based on experiments and information believed reliable. However, we can make no guarantee on performance of, or results obtained through the use of the product herein described owing to varying conditions in laboratories and plants over which we have no control. Neither can any guarantee be given that the products or uses outlined will not infringe any existing patents.

**Technical Specifications:**

|                           |                            |
|---------------------------|----------------------------|
| Appearance                | Opaque liquid              |
| Colour                    | White                      |
| Odour                     | Acrylic                    |
| Specific Gravity          | 1.005 – 1.045              |
| pH                        | 7.0 – 9.5                  |
| Refractive Index (% Brix) | 22.0 – 24.0%               |
| Coverage                  | 200 square meters/4 liters |